



# MC-Color Flair vision

High-performance pigmented coating with integrated easy-to-clean-technology

## Product Properties

- Two-component, water-based polyurethane-polymer combination
- Open to water vapour diffusion and carbonation-retarding
- Colour-proof as resistant to UV and weathering
- Resistant to elevated temperatures, frost and de-icing salts
- According to DIN EN ISO 11998 - wet abrasion resistance class 1
- According to DIN EN ISO 11998 - cleanability: parameter 0
- According to DIN EN ISO 2813 - gloss level 40 - 60
- Certified in accordance with ZTV-ING, TL/TP AGS-concrete
- Non-flammable, building material class A2-s1, d0 according to EN 13501-1 (product system test)
- Application by roller and airless spraying
- Certified and approved in accordance with DIN V 18026 as OS 2 and OS 4 system
- Certified in accordance with EN 1504 part 2

## Areas of Application

- Preventive concrete protection for exterior surfaces exposed to weathering
- Certified surface protection for traffic structures (bridge, tunnel)
- Surface protection for non-accessible and non-driven-on exterior areas
- Permanent protection system against graffiti and colour staining
- REACH-assessed exposure scenarios: periodical water-contact, periodical inhalation, application
- Certified in accordance with EN 1504 part 2 for principles 1, 2 and 8, procedure 1.3, 2.2, 8.2
- Resistant to frost and de-icing salts

## Application

### Substrate preparation

See leaflet "General Application Advice - Surface Protection Systems" and "Anti-graffiti Protection Systems".

If MC-Color Flair vision is used in combination with fine fillers, the concrete substrate must be prepared in accordance with leaflet "General Application Advice Fine Fillers".

### Application

MC-Color Flair vision consists of base and hardener component supplied in pre-packed quantities. Prior to application both components are mixed thoroughly using a slowly rotating mixer. Following mixing MC-Color Flair vision is filled into a clean container and stirred again.

After mixing is completed MC-Color Flair vision is applied crosswise, evenly and streak-free using a short-pile roller.

Alternatively MC-Color Flair vision can be applied by airless spraying.

For spray application please request our equipment planner "Airless".

Application must not proceed during rain, high humidity, frost or risk of frost. Freshly applied layers must be protected from dew, rain and frost.

### Overcoating times

MC-Color Flair vision is generally applied in two layers. If MC-Color Flair vision is used in combination with Nafufill KM 103 or Nafufill SF, it may only be overcoated after 24 hours at the earliest. If MC-Color Flair vision is used in combination with Emcephob WM we recommend an overcoating time of 12 - 24 hours.

Please observe the surface roughness surcharges indicated in the Application Advice.

### Graffiti removal

Best cleaning results are achieved, when graffiti are removed within the first 72 hours. Please see the technical data sheet and the EU-safety data sheet for MC-Cleaner G.





## Technical Data MC-Color Flair vision

Characteristic	Unit	Value*	Comments
Density	kg/dm <sup>3</sup>	1.21	
Solid content volume	Vol. %	49.7	
Mixing ratio	p.b.w.	10 : 3.5	base : hardener
Application time	hour	1	
Curing time	hours days	approx. 4 approx. 7	touch-dry resistant (graffiti)
Coverage**	g/m <sup>2</sup>	2 x 200	colour change recommended
Diffusion resistance against carbon dioxide	m	677	at 154 µm dry layer thickness
against water vapour	m	0.81	at 154 µm dry layer thickness
Rain-proof	hours	approx. 6	depending on temperature
Overcoating time***	hours	min. 4 max. 120 min. 3 max. 72	MC-Color Flair vision on MC-Color Flair vision (at + 20 °C) MC-Color Flair vision on MC-Color Flair vision (at + 30 °C)
Application conditions	°C °C % K	≥ 8 - ≤ 30 ≥ 15 - ≤ 25 ≤ 80 3	air- and substrate temperature MC-Color Flair vision relative humidity above dew point

## Product Characteristics MC-Color Flair vision

Delivery	10 kg and 30 kg
Calculated spreading rate**	10 kg (for 2 work steps) approx. 25 m <sup>2</sup> 30 kg (for 2 work steps) approx. 75 m <sup>2</sup>
Storage	Can be stored in original unopened packs for at least 12 months in cool and dry conditions. Protect from frost!
Disposal	Packs must be emptied completely.
EU-regulation 2004/42 (Decopaint-standard)	RL2004/42/EG All/j (140 g/l) < 140 g/l VOC

\* All technical data are lab values and relate to + 23 °C and 50 % relative humidity, the material temperature was between + 15 °C and + 25 °C.

\*\* Coverage rates depend on roughness, absorbency and type of substrate.  
To determine the project-specific coverage we recommend applying a trial area.

\*\*\* If overcoating times are exceeded the base coat must be slightly abraded.

**Note:** The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition 02/17. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.

②

MC-Bauchemie • Am Kruppwald 1-8 • 46238 Bottrop • Tel. +49 (0) 20 41-101 10 • Fax: +49 (0) 20 41-101 188  
info@mc-bauchemie.de • www.mc-bauchemie.de

MC-Bauchemie Singapore Pte Ltd • 8 Kaki Bukit Ave 4 • Premier@Kaki Bukit • 06-19 • Tel : +65 6462 0362 • Fax : +65 6466 0205  
enquirysingapore@mc-bauchemie.com www.mc-bauchemie.sg